



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

October 17, 2019

Mr. Charles Griffin
CARNEGIE
110 North Centre Avenue
Rockville Centre, NY 11570

Reference: Laboratory Test Report
Lab Identification No. 38476
Invoice No. 69658

Dear Mr. Griffin:

One (1) fabric sample, identified as **PATTERN: DIGITAL PRINTED SHEER**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

| <u>Specimen Number</u> | <u>Test Results</u> | |
|------------------------|------------------------------------|---------------------------------|
| | <u>Residual Flame</u> (seconds) | <u>Weight Loss</u> (percent) |
| 1 | 0.0 | 31.03 |
| 2 | 0.0 | 28.42 |
| 3 | 0.0 | 24.66 |
| 4 | 0.0 | 21.11 |
| 5 | 0.0 | 28.72 |
| 6 | 0.0 | 30.72 |
| 7 | 0.0 | 27.61 |
| 8 | 0.0 | 28.43 |
| 9 | 0.0 | 28.00 |
| <u>10</u> | <u>0.0</u> | <u>19.06</u> |
| AVG | 0.0 | 26.78 |

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

