

**Textile Testing**553 76th Street - Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 51505

Date: 11-05-2012

For the Account Of: Carnegie
 110 North Centre Avenue
 Rockville Center, NY 11570

Contact: Charles Griffin

Client's Identification: Crossing 4356

Test Performed NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition
 Resistance of Components of Upholstered Furniture – 2003 and UFAC Fabric
 Classification Test Method – 1990

TEST DATA

Specimen #	Char Length (Inches)
1	Self Extinguished
2	Self Extinguished
3	Self Extinguished

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 44 mm (1.75 in.) or less, the fabric is classified a UFAC and NFPA Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.), the fabric is classified a UFAC Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a UFAC Class II cover fabric.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested is:

- Class I
 Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

C. Venturini

Authorized Signature-MB