

**Textile Testing**553 76<sup>th</sup> Street - Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119

Report Number: 51505

Date: 11-05-2012

For the Account Of: Carnegie  
 110 North Centre Avenue  
 Rockville Center, NY 11570

Contact: Charles Griffin

---

 Client's Identification: Journey 6292
 

---

**Test Performed** NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition  
 Resistance of Components of Upholstered Furniture – 2003 and UFAC Fabric  
 Classification Test Method – 1990

**TEST DATA**

Specimen #	Char Length (inches)
1	Self Extinguished
2	Self Extinguished
3	Self Extinguished

**NOTES**

**Test Conditions:** 70 ±2°F, 65 ±2% Relative Humidity

**ACCEPTANCE CRITERIA**

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 44 mm (1.75 in.) or less, the fabric is classified a UFAC and NFPA Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.), the fabric is classified a UFAC Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a UFAC Class II cover fabric.

**CONCLUSION**

Based on the above Results and Acceptance Criteria, the item tested is:

- Class I  
 Class II

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature: 