

DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 1, 2011

Mr. Charles Griffin
CARNEGIE
110 North Centre Avenue
Rockville Centre, NY 11570

Reference: Laboratory Test Report
Lab Identification No. 7940
Invoice No. 29444 (Attached)

Dear Mr. Griffin:

One (1) fabric sample, identified as **PATTERN: 4442; CONTENTS: 100% TREVIRA CS**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	25.80
2	0.0	26.00
3	0.0	23.75
4	0.0	20.98
5	0.0	18.09
6	0.0	6.20
7	0.0	27.19
8	0.0	22.95
9	0.0	22.46
10	0.0	14.28
AVG.	0.0	20.77


The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
Attachment



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 1, 2011

Mr. Charles Griffin
CARNEGIE
110 North Centre Avenue
Rockville Centre, NY 11570

Reference: Laboratory Test Report
Lab Identification No. 7940
Invoice No. 29444 (Attached)

Dear Mr. Griffin:

One (1) fabric sample, identified as **PATTERN: 4442; CONTENTS: 100% TREVIRA CS**, was received and tested in accordance with AATCC Test Method 96-2009, "Dimensional Changes in Commercial Laundering of Woven and Knit Fabrics Except Wool". The conditions used were: Wash Temperature: (IVc) 160F; Drying Procedure: (A) Tumble; Restoration: (0) None. The test results are as follows:

<u>% Dimensional Change</u>			
<u>1st Cycle</u>		<u>5th Cycle</u>	
<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>
0.0	0.0	0.3	0.2

<u>Durable Press Rating*</u>	
<u>1st Cycle</u>	<u>5th Cycle</u>
4	4

* 4 - Smooth, finished appearance.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
Attachment